

## TECHNICAL DATA

# MONO<sup>®</sup>

## MONO ULTRA<sup>™</sup> BATH & KITCHEN SEALANT

Revised: 3/25/10

### MONO Ultra<sup>®</sup> Bath & Kitchen Aerosol Sealant – White

- **NO CAULK GUN NEEDED!**
- **Waterproof Seal**
- **Mildew Resistant**
- **Easy water clean-up**
- **Paintable**
- **Superior Adhesion**
- **Skins Quickly**
- **Low Odour**

**Packaging:** 200 mL can  
**Color:** White  
**DAP UPC Number:** 0 70798 75769 1  
**MONO Product Code:** 0 63213 00769 3  
**MONO Model:** 967806102

#### Company Identification:

Manufactured For: DAP Canada, 475 Finchdene Square, Unit 5, Scarborough, ON M1X 1B7  
Usage Information: Call 1-888-327-8477 or visit [monosealants.ca](http://monosealants.ca)  
Order Information: 416-321-1522  
Fax Number: 416-321-3325

#### Product Description:

**MONO Ultra<sup>®</sup> Bath & Kitchen Aerosol Sealant** applies right from the tube – NO CAULK GUN NEEDED! Latex-based sealant that provides a durable, waterproof seal in bathroom and kitchen applications. Low odour, mildew resistant, outstanding flexibility and superior adhesion. Paintable and cleans up easily with soap and water.

#### Suggested Uses:

*Ideal for Caulking and Sealing:*

- *Showers*
- *Acrylic shower inserts*
- *Sinks*
- *Tubs*
- *Countertops*
- *Backsplashes*
- *Bathroom fixtures*
- *Kitchen fixtures*
- *Toilets*

*Outstanding adhesion to:*

- *Ceramic Tile*
- *Porcelain*
- *Metal*
- *Painted Surfaces*
- *Plastic Tile*
- *Cultured Marble*
- *Drywall*
- *Glass*
- *Wood*
- *Fiberglass*

### **Surface Preparation & Application:**

1. All surfaces must be clean, dry and completely free of old caulk.
2. Do not use for water-submerged applications.
3. Apply at temperatures above 5°C (40°F).
4. Remove cap, screw on nozzle/trigger fixture (included), clockwise until snug.
5. Hold can in any direction (360° application). Place nozzle tip firmly against joint and then press trigger.
6. Match the movement of the nozzle with the speed of the material flow to achieve desired bead size.
7. Fill gap with sealant.
8. Smooth bead.
9. Joint width should not exceed 9.5 mm (3/8"). If joint depth exceeds 9.5 mm (3/8"), use backer rod material.
10. Clean up excess uncured sealant with damp sponge before it skins over. Scrape or cut away excess cured sealant.
11. Allow sealant to dry at least 2 hours (longer in cool/humid conditions) before painting with a latex or oil-based paint.
12. Remove nozzle/trigger and rinse it and valve stem with warm water for storage and re-use.

#### *For best results:*

- *Apply in temperatures above 5°C (40°F).*
- *Not for continuous underwater use.*
- *Allow sealant to dry fully (at least 24 hours) before exposing to water and moisture.*
- *Store product away from extreme heat or cold.*

### **Physical & Chemical Characteristics:**

Tooling Time:	10 minutes
Tack Free Time:	30 minutes
Paintable:	Yes
Odor:	Very Mild
Consistency:	Smooth and Creamy
Vehicle:	Acrylic Polymer
Volatile:	Water
Flash Point:	None
Filler:	Calcium Carbonate
Density:	1.05 ± 0.01
Solids:	59% ± 1.0% by weight
Weight per Gallon:	1.05 ± .01 kg/L (8.8 ± 0.05 lbs/gal)
Service Temperature:	-34°C to 82°C (-30°F to 180°F)
Application Temperature:	4°C to 38°C (40°F to 100°F)
Freeze Thaw Stability:	Passes 5 Cycles
Shelf Life:	12 Months
Coverage:	11 metres at 4.76 mm bead (36 linear ft. at a 3/16" diameter bead) or 2 average size bathtubs.
MSDS No:	00042395603

**Clean Up:**

Before curing, remove excess sealant with a damp cloth. After product has cured, excess sealant must be cut or scraped away.

**Safety:**

See product label or Material Safety Data Sheet (MSDS) for safety information. You can request an MSDS by visiting our website at [monosealants.ca](http://monosealants.ca) or by calling 416-321-1522.

**Satisfaction Guarantee:**

If not satisfied with product performance when used as directed within one year of purchase, DAP Canada will replace this product or refund your purchase price. Call 416-321-1522 with your sales receipt and product container available to arrange for warranty fulfillment. DAP Canada and its affiliates will not be liable for any incidental or consequential damages under any circumstances.